

International Journal of Production Management and Engineering



Editorial
Universitat Politècnica
de València

I
J
PME  **International Journal of
Production Management
and Engineering**

Volume 7(2)
2019
Pages 117-159



EDITOR IN CHIEF

Prof. Josefa Mula Bru, Universitat Politècnica de València, Spain

EDITORS

Dr. Andrés Boza, Universitat Politècnica de València, Spain

Dr. Llanos Cuenca, Universitat Politècnica de València, Spain

Dr. Pedro Gómez-Gasquet, Universitat Politècnica de València, Spain

Prof. Eduardo Vicéns-Salort, Universitat Politècnica de València, Spain

EDITORIAL BOARD

Prof. Marija Bogataj, University of Ljubljana, Slovenia

Dr. Bernardo Almada-Lobo, Universidade do Porto, Portugal

Dr. David Bogataj, University of Padova, Italy

Prof. Luis M. Camarinha-Matos, New University of Lisbon, Portugal

Dr. Francisco Campuzano-Bolarín, Universidad Politécnica de Cartagena, Spain

Prof. Luiz C. R. Carpinetti, University of Sao Paulo, Brazil

Prof. Ramón Companys Pascual, Universitat Politècnica de Catalunya, Spain

Dr. Manuel Díaz-Madroño, Universitat Politècnica de València, Spain

Prof. Alexandre Dolgui, IMT Atlantique, France

Prof. Bernard Grabot, University of Toulouse, France

Dr. Susan Grant, Brunel University, United Kingdom

Prof. Paul W. P. J. Grefen, Eindhoven University of Technology, Netherlands

Dr. Luis Guimarães, Universidade do Porto, Portugal

Dr. Jorge E. Hernandez, University of Liverpool Management School, United Kingdom

Prof. Cesáreo Hernández Iglesias, Universidad de Valladolid, Spain

Prof. Roland Jochem, Fraunhofer - Institute for Production Systems and Design Technology, Germany

Prof. Francisco C. Lario Esteban, Universitat Politècnica de València, Spain

Prof. Andrew C.L. Lyons, University of Liverpool Management School, United Kingdom

Prof. Luis Onieva Giménez, Universidad de Sevilla, Spain

Prof. Angel Ortiz Bas, Universitat Politècnica de València, Spain

Prof. Raúl Poler, Research Centre on Production Management and Engineering Universitat Politecnica de Valencia, Spain

Prof. José Carlos Prado-Prado, Universidad de Vigo, Spain

Dr. Raquel Sanchis, Universitat Politècnica de València, Spain

Prof. François Vernadat, European Court of Auditors, France

PUBLISHED BY

Editorial Universitat Politècnica de València

SUBSCRIPTION INFORMATION

Editorial Universitat Politècnica de València, pedidos@editorial.upv.es

Price: 15 € / issue

LAYOUT

Enrique Mateo, Triskelion disseny editorial

COVER DESIGN

Francisco Javier Boza García

ISSN 2340-5317

EISSN 2340-4876

Depósito Legal V-1737-2013

Table of contents

PAPERS

Modelling inventory management: Separate issues for construction and application.....	117
Luchko, M.R., Lukanovska, I.R., Ratynskyi, V.	
An Analysis of Implementation of Taguchi Method to Improve Production of Pulp on Hydrapulper Milling	125
Hernadewita, Rochmad, I., Hendra, Hermiyetti, Yuliani, E.N.S.	
Effect of routing flexibility on the performance of manufacturing system	133
Khan,W.U., Ali, M.	
Performance measurement in Judo: main KPIs, cluster categorization and causal relationships.....	145
Uriarte Marcos, S., Rodríguez-Rodríguez, R., Uriarte Marcos, M., Alfaro-Saiz, J.J.	
Developing a Novel Based Productivity Model by Investigating Potential Bounds of Production plant.....	151
Hussain, Z.	

An Analysis of Implementation of Taguchi Method to Improve Production of Pulp on Hydrapulper Milling

Hernadewita^a, Rochmad, I.^b, Hendra^c, Hermiyetti^d, Yuliani, E.N.S.^e

^{a,b,c} Magister of Industrial Engineering, Mercu Buana University, Jl. Meruya Selatan, Jakarta, Indonesia

^c Mechanical Engineering, University of Bengkulu, Jl. Kandang Limun, Bengkulu, Indonesia.

^d Faculty of Economic Social Science, Bakrie University, Jl. HR Rasuna Said, Jakarta Selatan, Indonesia.

^ahernadewita@mercubuana.ac.id, ^bimb_rochmad@yahoo.co.id

Abstract: Taguchi method is one of a design of experimental (DOE), by using statistical approach to optimize the process parameters and maintaining the minimum variability and also improve the quality of product. Based on data characterisation, Nominal is Best in Taguchi methods is suitable application in this study. Its describe the procedures and steps that occur in DOE to find an optimum quality parameter corresponding quality characterisation. Nominal is the best applied in milling process of pulp on the hydrapulper with pulp freeness 650 Canadian Standard Freeness (CSF). The result is shown by orthogonal array, Signal-to-Noise (S/N) Ratio and analysis of variances (ANOVA). Three factors considered in this study and namely the composition of pulp (waste paper), pulp consistency and milling time. The experiment will conducted after determination of each level and the appropriate orthogonal array was selected. After measuring of pulp freeness produced by the pulp milling on the hydrapulper, then Signal-to-Noise (S/N) Ratio is calculated. As the conclusion, the factors and levels of optimum freeness obtained, pulp composition in level 1 (100%), pulp consistency at level 2 (8%) and milling time factor in level 2 (45 minutes). The result of experimental verification was interpreted in the conclusion.

Key words: Taguchi, DOE, pulp, hydrapulper, Nominal is the Best, ANOVA.

1. Introduction

In the globalization era, the competition among the business is very tight. One is shown by the development of materials input in industry. Its indicated by arising on launching the new products with variety of brands into the market, either national and international. In such situation, the main problem needs to be solve by businesses in order to survive is by giving focused on satisfaction to customers compared to the other factors.

There is no doubt that the main factor determining of customer satisfaction is the quality of product or services. Organizations or companies which meet quality requirement of products and services will be satisfying the customer needs. In fullfulness of

customer satisfaction, as one of the fiber cement company in Indonesia, PT. BBI is committed to constantly improve their competitiveness and seize in a larger market, thus increasing in the quality of products and services as one of the determinants factor of customer satisfaction.

As one of the flagship products of PT. BBI is a corrugated fiber cement, which is produced in Sheet Machine, Line I to IV. Which is one of main content are milled pulp in hydrapulper with specific freeness of 650 Canadian Standard Freeness (CSF). The freeness of the pulp mill on hydrapulper currently very varietive, so that, it will have an impact to overall quality of fiber cement for corrugating roof. To improve the quality of the pulp production, so then, its conducted Taguchi experimental design

To cite this article: Hernadewita, Rochmad, I., Hendra, Hermiyetti, Yuliani, E.N.S. (2019). An Analysis of Implementation of Taguchi Method to Improve Production of Pulp on Hydrapulper Milling. *International Journal of Production Management and Engineering*, 7(2), 125-131. <https://doi.org/10.4995/ijpme.2019.10163>

approach with characterisation of quality by nominal is the best, in achieving the freeness of milled pulp of 650 CSF.

The objectives in this study was to determine the factors that influence the quality of the pulp slurry freeness and examine of each level of optimal factor for the improvement of the quality of the pulp milling on the hydrapulper.

2. Taguchi Method

This study is used an experimental design approach with the application of Taguchi method. Taguchi method is one of a new method in the field of engineering that objectives to improve the quality of products and processes and the mean time will costs and resources to a minimum (Taguchi, 1993; Kawamura, 2010). The objective of Taguchi method is to meet the product robust against noise, as it is often referred as the Robust Design. Robust Design method, also called the Taguchi Method, pioneered by Dr. Genichi Taguchi, greatly improves engineering productivity. By consciously considering the noise factors (environmental variation during the product's usage, manufacturing variation, and component deterioration) and the cost of failure in the field the Robust Design method helps ensure customer satisfaction. Robust Design focuses on improving the fundamental function of the product or process, thus facilitating flexible designs and concurrent engineering. Indeed, it is the most powerful method available to reduce product cost, improve quality, and simultaneously reduce development interval. As the definition of quality according to Taguchi is loss received by the public since the product was shipped. Taguchi's philosophy of quality consists of four concepts (Taguchi, 1993), as:

1. Quality should be designed into the product and not just doing control by quality check.
2. The best quality is achieved by minimising the deviation from the target.
3. Products must be designed to be robust against environmental factors that could not be controlled.
4. The cost of quality should be measured in a function of a certain standard deviation, so that the loss should be measured in the whole system.

Taguchi method characterise as off-line quality control, which means as preventive quality control in product design or production process before arriving

at the shop floor level. Off-line quality control is determined at the beginning of the life cycle of product improvement at the beginning of the product (to get right first time). Taguchi contribution to quality are:

1. Loss Function: Represents the loss produced by the people (producers and consumers) due to the quality produced. For producers with the cost of quality carried out by customers is their dissatisfaction or frustration of products purchased or used because of poor quality.
2. Orthogonal Array: Used to design an experiment that efisisen and used to analyze experimental data. Orthogonal array is used to determine the minimum number of experiments that can give as much information as possible all factors that influence the parameter. The most important part of the orthogonal array lies in the selection level combination of input variables for each experiment.
3. Robustness: Minimizing the sensitivity of the system to the sources of variation.

2.1. Taguchi Design of Experiments

Taguchi experimental design is an assessment simultaneously to two or more factors (parameters) affecting the ability of the average or the variability of the combined results of the features of the product or process. Some of the steps proposed by Taguchi to experiment systematically, namely:

- a. Formulation of the problem
- b. Experimental purposes
- c. Determination of the dependent variable
- d. Identify the factors (independent variables)
- e. Separation of control factors and noise factors
- f. Specifies the number of levels and the level of each factor
- g. The calculation of degrees of freedom
- h. Selection of an orthogonal matrix
- i. Placement of the factors and the interaction space into an orthogonal array
- j. Implementation of the experiment according to an orthogonal array
- k. Analyzing the experimental data with ANOVA, calculate the optimal quality prediction .
- l. The implementation of the verification experiment.

Table 2.1. Determination of Total Level and Level Value Factor.

Code	Control Factors	Unit	Level 1	Level 2	Level 3
A	Pulp composition (waste paper)	%	100	90	80
B	Pulp Consistency	%	4	8	12
C	Milling time	minute	30	45	60

Table 2.2. Results of experiments with orthogonal array $L_{27}(3^{13})$.

Experiment	Factors dan Interaction													Replication (CSF)			Total	Mean
	1	2	3	4	5	6	7	8	9	10	11	12	13	1	2	3		
	A	B	AxB(1)	AxB(2)	C	AxC(1)	AxC(2)	e	e	e	e	e	e					
1	1	1	1	1	1	1	1	e	e	e	e	e	e	640	630	640	1910	636.667
2	1	1	1	1	2	2	2	e	e	e	e	e	e	610	620	630	1860	620.000
3	1	1	1	1	3	3	3	e	e	e	e	e	e	620	610	620	1850	616.667
4	1	2	2	2	1	1	1	e	e	e	e	e	e	660	670	660	1990	663.333
5	1	2	2	2	2	2	2	e	e	e	e	e	e	660	650	650	1960	653.333
6	1	2	2	2	3	3	3	e	e	e	e	e	e	610	630	620	1860	620.000
7	1	3	3	3	1	1	1	e	e	e	e	e	e	690	680	690	2060	686.667
8	1	3	3	3	2	2	2	e	e	e	e	e	e	660	660	670	1990	663.333
9	1	3	3	3	3	3	3	e	e	e	e	e	e	630	650	640	1920	640.000
10	2	1	2	3	1	2	3	e	e	e	e	e	e	670	690	670	2030	676.667
11	2	1	2	3	2	3	1	e	e	e	e	e	e	650	650	670	1970	656.667
12	2	1	2	3	3	1	2	e	e	e	e	e	e	640	630	630	1900	633.333
13	2	2	3	1	1	2	3	e	e	e	e	e	e	680	670	670	2020	673.333
14	2	2	3	1	2	3	1	e	e	e	e	e	e	660	650	680	1990	663.333
15	2	2	3	1	3	1	2	e	e	e	e	e	e	640	620	630	1890	630.000
16	2	3	1	2	1	2	3	e	e	e	e	e	e	690	690	710	2090	696.667
17	2	3	1	2	2	3	1	e	e	e	e	e	e	680	670	660	2010	670.000
18	2	3	1	2	3	1	2	e	e	e	e	e	e	640	650	640	1930	643.333
19	3	1	3	2	1	3	2	e	e	e	e	e	e	680	670	680	2030	676.667
20	3	1	3	2	2	1	3	e	e	e	e	e	e	660	660	660	1980	660.000
21	3	1	3	2	3	2	1	e	e	e	e	e	e	640	630	630	1900	633.333
22	3	2	1	3	1	3	2	e	e	e	e	e	e	680	680	700	2060	686.667
23	3	2	1	3	2	1	3	e	e	e	e	e	e	660	660	670	1990	663.333
24	3	2	1	3	3	2	1	e	e	e	e	e	e	630	640	630	1900	633.333
25	3	3	2	1	1	3	2	e	e	e	e	e	e	710	700	690	2100	700.000
26	3	3	2	1	2	1	3	e	e	e	e	e	e	680	680	670	2030	676.667
27	3	3	2	1	3	2	1	e	e	e	e	e	e	650	670	670	1990	663.333
Average																	656.914	

3. Result

Based on Taguchi experimental and the result to the orthogonal array, the data processed came out as follows:

Table 3.2. Factors Interaction Solutions A and B.

Interaction	B ₁	B ₂	B ₃
A ₁	624.444	645.556	663.333
A ₂	655.556	655.556	670.000
A ₃	656.667	661.111	680.000

Table 3.1. Response Pulp Freeness Average of Factors Effect.

	A	B	(AxB)1	(AxB)2	C	(AxC)1	(AxC)2
Level 1	644.444	645.556	651.852	653.333	677.407	654.815	656.296
Level 2	660.370	654.074	660.370	657.407	658.519	657.037	656.296
Level 3	665.926	671.111	658.519	660.000	634.815	658.889	659.259
Variance	21.481	25.556	8.519	6.667	42.593	4.074	2.963
Rank	3	2	4	5	1	6	7

To reach the intended target (nominal is the best), the determination of the optimal factor level is the result on the test that approach the pulp freeness on 650 CSF. So that, the optimal combination of factors level are:

- A1 = Waste paper 100%.
- B2 = Pulp Consistency 8%.
- C2 = Milling time for 45 minutes.

The percentage contribution from the Table 3.4 shows that the factor C (milling time) was contributed to the most of average freeness of the pulp, which 55.205% followed by factor B (consistency) 20.084% and factor A (waste paper) 14.561%.

To obtain the target of nominal is the best, combination of optimal factor level achieved in the average value of S/N ratio is the lowest level of each factor, indicating the smaller of the value closer to the target. The optimum level factors are:

- A1 = Waste paper 100%.
- B2 = Pulp Consistency 8%.
- C2 = Milling time for 45 minutes.

3.1. Analysis of Varians (ANOVA) S/N Ratio Pulp Freeness Average

The ANOVA for S/N Ration Pulp Freeness Average is shown of Table 3.7 and Table 3.8:

Table 3.3. Analysis of Variance Combined Pulp Freeness Average.

Sources	v	SS	MS	F - Ratio	F- Table
A	2	2,237.860	1,118.930	21.839	3.007
B	2	3,047.737	1,523.868	29.743	3.007
AxB(1)	4	361.317	90.329	1.763	3.007
AxB(2)			Pooled (III)		
C	2	8,198.354	4,099.177	80.008	3.007
AxC(1)			Pooled (II)		
AxC(2)			Pooled (I)		
Error	16	819.753	51.235	-	-
Total	26	14,665.021	-	-	-

Table 3.4. Percentage Contribution.

Sources	v	SS	MS	SS'	p(%)
A	2	2,237.860	1,118.930	2135.391	14.561
B	2	3,047.737	1,523.868	2945.267	20.084
AxB(1)	4	361.317	90.329	156.379	1.066
C	2	8,198.354	4,099.177	8095.885	55.205
Error	16	819.753	51.235	-	-
Total	26	14,665.021	-	-	-

Table 3.5. Response S / N Ratio Pulp Freeness of Factors Effect.

	A	B	(AxB)1	(AxB)2	C	(AxC)1	(AxC)2
Level 1	25.986	26.238	27.232	28.289	29.343	24.717	25.741
Level 2	26.709	25.922	26.399	25.045	24.549	26.404	26.412
Level 3	26.971	27.506	26.033	26.332	25.774	28.544	27.728
Variance	0.985	1.584	1.199	3.244	4.794	3.827	1.987
Rank	7	5	6	3	1	2	4

Table 3.6. Factors Interaction Solutions.

Interaction	B ₁	B ₂	B ₃	Interaction	C ₁	C ₂	C ₃
A ₁	28.079	23.686	26.191	A ₁	26.121	23.686	28.150
A ₂	26.013	27.287	26.826	A ₂	30.303	25.877	23.947
A ₃	24.621	26.791	29.499	A ₃	31.604	24.084	25.224

Table 3.7. Analysis of Variance Combined S/N Ratio Pulp Freeness.

Sources	v	SS	MS	SS'	ρ(%)
B	2	12.649	6.325	-19.567	-4.217
AxB(2)	4	48.029	12.007	-16.405	-3.535
C	2	111.667	55.834	79.450	17.121

Table 3.8. Percent contribution of S/N Ratio Pulp Freeness.

Sources	v	SS	MS	F-Ratio	F-Table
A	Pooled I				
B	2	12.649	6.325	0.393	3.112
AxB(1)	Pooled II				
AxB(2)	4	48.029	12.007	0.745	3.112
C	2	111.667	55.834	3.466	3.112
AxC(1)	4	66.2	16.55	1.027	3.112
AxC(2)	Pooled III				
Error	14	225.518	16.108	-	-
Total	26	464.064	-	-	-

The percentage contribution from the Table 3.7 and 3.8, shows that the factor C (milling time) contributed to the most of average freeness of the pulp, which is 17.121% followed by interaction of factors AXC (1) 0.381% and an average interaction AXB (2) -3.535%.

4. Conclusions and Discussion

As the definition of pulp freeness on milling process is spread/decomposition of pulp fibers after the milling process, the measuring standard of freeness on industry are generalise in three types, such as; Canadian Standard freeness (CSF), Schopper Riegler (°SR) and Williams Slowness (s).

Table 4.1. Interpretation of Measurement Results of Pulp Freeness Average.

Pulp freeness Average	Prediction	Optimize
Taguchi Average (m)	643.210	643.210±4.380
Experimental S/N Variability	22.589	22.589±3.524
Verification Average (m)	646.210	646.210±6.829
Experimental S/N Variability	15.589	15.589±7.860

As the result from Taguchi experimental, it shown that the freeness of pulp produced from hydrapulper milling prediction increasing the quality. Also, as the experimental verification data showed an increasing in the quality of milling process significantly and the freeness of the pulp milled on hydrapulper more stable.

4.1. Research limitations

The accuracy of the results was strongly influenced by the chosen of the instruments. The suitable




Figure 4.1. The Current Pulp Freeness Produced from Hydrapulper Milling.




Figure 4.2. The Pulp Freeness Produced from Hydrapulper Milling On Experimental Verification

measuring instruments will be determining the accuracy on the result of study. Furthermore, reference to relevant support, with the access to reference study related will facilitate the next coming research in the same field and differences method and instruments. Number of limitations in the this study, are:

1. The measurement scale on range was used a multiply of 10. So that, the measuring results are less accuracy on readings than compared to the results of calculations verification on Taguchi experimental.
2. The lack of references on this study. In this study there was little impediment as a comparison. Furthermore, the comparison was used cross references study in the sense of the pulp.

The Taguchi design experimental is considered into the factors that influence the quality characterization, without considering to the interference factors. Thus, the experiment was focused on the implementation of complexity and significant costs. As the engine noise is not included in this study, the effect of engine noise also can affect the accuracy and quality of experimental results.

5. Conclusion and Discussion

5.1. Conclusion

1. The quality improvement of the pulp freeness produced from hydropulper milling was shown by Taguchi experimental design implementation

with the character of nominal is the best (650 CSF). The obtained factors and the level of each factors that influence the pulp freeness produced from hydropulper milling processing, as follows:

- a. The composition of recycled paper (waste paper) at the level 1 (100%).
 - b. Pulp consistency at level 2 (8%).
 - c. Milling time at level 2 (45 minutes).
2. The use of recycled paper of cement bags (waste paper) is decreased the production cost of the fiber cement roofing. As the price of recycled paper of cement bags are generally cheaper than new paper that used as an imported, and at the same time maintaining appropriate quality standards.

5.2. Discussion

In addition to the conclusions, the recommendation on more accurate and detail of experimental results to quality improvement are as follows:

1. Carefully use a measuring tube with a scale size and clearly, will avoid errors in reading, so it will produce accurate information or data that used as the experimental results.
2. The use of Taguchi experimental design can be developed, such as in engineering tests to find the best product quality in manufacturing line. And also improved the quality of product for fiber cement roofing and other products are affected by several factors and levels.

References

- Athreya, S., Venkatesh, Y.D. (2012). Application Of Taguchi Method For Optimization Of Process Parameters In Improving The Surface Roughness Of Lathe Facing Operation. *International Refereed Journal of Engineering and Science (IRJES)*. 1(3), 13-19.
- Bellavendram, N. (1995). *Quality by Design: Taguchi Techniques for Industrial Experimentation*. Prentice Hall, London.
- Cho, B. U., Ryu, J.Y., Song, B.K. (2008). Pilot Study on the Manufacture of Kraft Paper from OCC. *Journal of Korea Technical Association of The Pulp and Paper Industry*, 40(5), 27-35.
- Daoning, Y., Hong, L. (2016). Fluidization Characteristics of Medium-High-Consistency Pulp Fiber Suspensions with an Impeller. *International Journal of Rotating Machinery Volume 2016*. Hindawi Publishing Corporation. Article ID 3902723, 8 pages. <https://doi.org/10.1155/2016/3902723>
- Dobrzański, L.A. (2007). Application of Taguchi Method in The Optimisation of Filament Winding of Thermoplastic Composites. *International Scientific Journal*, 28(3). Published monthly as the organ of the Committee of Materials Science of the Polish Academy of Sciences.
- Fatoki, J.G., Omoniyi, T.E., Onilude, M.A. (2015). Design and Fabrication of a Hydropulper for Disintegrating Disused Tetra Pack® Beverage Cartons. *European International Journal of Science and Technology*, 4(6), 113-123.
- Gharehkhani, S., Sadeghinezhad, E., Kazi, S.N., Yarmand, H., Badarudin, A., Safaei, M.R., Zubir, M.N.M. (2015). Basic Effects of Pulp Refining on Fiber Properties - A Review. *Carbohydrate polymers*, 115, 785-803. <https://doi.org/10.1016/j.carbpol.2014.08.047>

An Analysis of Implementation of Taguchi Method to Improve Production of Pulp on Hydrapulper Milling

- Hassan, K., Kumar, A., Garg, M.P. (2012). Experimental Investigation of Material Removal Rate in CNC Turning Using Taguchi Method. *International Journal of Engineering Research and Applications*, 2(2), 1581-1590.
- Iosip, A., Nicu, R., Ciolacu, F., Bobu, E. (2010). Influence of Recovered Paper Quality on Recycled Pulp Properties. *Cellulose Chemistry & Technology*, 44(10), 513.
- Juran, J.M., Godfrey, A.B. (1998). *Juran's Quality Handbook*. 5th Edition. A Division of The McGraw-Hill Companies. USA.
- Kamarudin, S., Zahid, A., Wan, K.S. (2004). The Use of taguchi Method In Determining The Optimum Plastic Injection Moulding Parameters For The Production of A Consumer Product. *Jurnal Mekanikal*. Desember 2004, Bil.18, 98-110.
- Kawamura, T. (2010). Performance Measures for Robust Design and Its Applications. *4th International Workshop on Reliable Engineering Computing (REC 2010)*. ISBN: 978-981-08-5118-7. Published by Research Publishing Services.
- Khalilitabas, A.A., Khorrami, M., Sobhani, J. (2009). Effects on Wood-pulp Fibers on The Mechanical Properties of Cement Composites. In *The 3rd International Conference on Concrete and Development*.
- Kumar, N.S., Simha, S.T.P. (2012). Experimental Investigation on Seismic Resistance of Recycle Concrete in Filled Steel Columns – Taguchi's Approach. *15 WCEE Lisboa*.
- Lajis, M.A., Radzi, H.C.D., Amin, A.K.M.N. (2009). The Implementation of Taguchi Method on EDM Process of Tungsten Carbide. *European Journal of Scientific Research*, 26(4), 609-617.
- Martin, N., Anglani, N., Einstein, D., Khrushch, M., Worrell, E., Price, L.K. (2000). *Opportunities to Improve Energy Efficiency and Reduce Greenhouse Gas Emissions in the US Pulp and Paper Industry*. Technical report. U.S. Department of Energy Office of Scientific and Technical Information <https://doi.org/10.2172/776606>
- Moretti, J.P., Mancini, S.D., Antunes, M.L.P., de Paiva, J.M.F. (2015). Recycling Scrap Automotive Heat Shield Insulation Material. *Journal of Material Cycles and Waste Management*, 17(1), 33-41. <https://doi.org/10.1007/s10163-013-0222-x>
- Nasir, M. (1999). *Metode Penelitian*. Ghalra Indonesia: Jakarta.
- Olutoye, M. A. (2005). Design of a Manually Operated Paper-Recycling Machine. *Leonardo Electronic Journal of Practices and Technologies*, 4(7), 49-54.
- Onilude, M.A., Omoniyi, T.E., Akinyemi, B.A. (2013). The Design and Fabrication of A Recycled Paper Egg Tray. *Amer. Int. Jou. of Cont. Res.*
- Roy, R.K. (2010). *A Primer on the Taguchi Method*. 2nd Edition. Society of Manufacturing Engineers. Dearborn: Michigan. USA.
- Selvaraj, D.P., Chandramohan, P. (2010). Optimization of Surface Roughness of AISI 304 Austenitic Stainless Steel in Dry Turning Operation Using Taguchi Design Method. *Journal of Engineering Science and Technology*, 5(3), 293-301.
- Siagian, D., Sugiarto (2006). *Metode Statistika Untuk Bisnis dan Ekonomi*. PT. Gramedia Pustaka Utama: Jakarta.
- Soejanto, I. (2009). *Desain Eksperimen Dengan Metode Taguchi*. Graha Ilmu: Yogyakarta.
- Taguchi, G. (1993). *Taguchi on Robust Technology Development: Bringing Quality Engineering Upstream*. Okhen Associates. Tokyo. Japan. ASME Press New York. <https://doi.org/10.1115/1.2905506>
- Teixeira, D.E. (2012). Recycled Old Corrugated Container Fibers for Wood-Fiber Cement Sheets. *International Scholarly Research Network. ISRN Forestry*. Volume 2012, Article ID 923413, 8 pages. <https://doi.org/10.5402/2012/923413>
- Verma, J., Agrawal, P., Bajpai, L. (2012). Turning Parameter Optimization for Surface Roughness of ASTM A242 Type-1 Alloys Steel by Taguchi Method. *International Journal of Advances in Engineering & Technology*, 3(1), 255-261.
- Worrell, E., Martin, N., Anglani, N., Einstein, D., Khrushch, M., Price, L. (2001). Opportunities to Improve Energy Efficiency in the US Pulp and Paper Industry. *Lawrence Berkeley National Laboratory*, 1-56.
- Yadav, U.K., Narang, D., Attri, P.S. (2012). Experimental Investigation and Optimization of Machining Parameters for Surface Roughness in CNC Turning by Taguchi Method. *International Journal of Engineering Research and Applications*, 2(4), 2060-2065. <http://www.ekodokcell.co.cc/2010/05/proses-pembuatan-pulp-dengan-proses.html> (accessed on December 23rd, 2016).
- <http://fandikasbara.wordpress.com> (Dzar, abu, (2009). Proses Pembuatan dan Pengolahan Limbah Industri Pulp, accessed on November 28th, 2016).
- <http://www.google.com/2011/07/makalah-pulp-and-paper.html> (accessed on November 26th, 2016).