

Emerging Trends in the Development of Chitosan Films for Active Food Packaging

by Dhena Ria Barleany

Submission date: 04-Apr-2023 06:58PM (UTC+0700)

Submission ID: 2055569248

File name: 10594-26899-1-PB.pdf (276.47K)

Word count: 3954

Character count: 22502

Emerging Trends in the Development of Chitosan Films for Active Food Packaging

Dhena Ria Barleany^{1*}, Denni Kartika Sari¹, Retno Sulisty Dhamar Lestari¹

6

¹Chemical Engineering Department, Faculty of Engineering, University of Sultan Ageng Tirtayasa, Jln. Jenderal Sudirman Km. 03, Cilegon, Banten, Indonesia

*Corresponding Author Email: ria.barleany@untirta.ac.id

ARTICLE HISTORY

13

Received July 23, 2020

Received in revised form September 24, 2020

Accepted October 16, 2020

Available online October 17, 2020

ABSTRACT

The demand for healthy and safe foods with the minimum use of synthetic materials is increasing very rapidly. Plastic polymers have negative effects on the environment, and great efforts have been made to evaluate the use of various bio-based polymers as alternatives to synthetic plastic packaging. Chitin and chitosan are mostly extracted from crustacean shells or by products from processing and handling fish and seafood. As a result, chitosan as a material for food packaging has received much attention and is widely researched because it has unique biological and functional properties. Chitosan for food packaging and food preservation applications can be applied via the method of spraying, immersing, coating, or wrapping films. However, chitosan has several disadvantages including low mechanical properties and high sensitivity to moisture, which are the main limitations for its industrial applications, including food packaging. In this study, the scientific literature of the last 5 years on chitosan-based films for their potential application in the food packaging industry has been extensively reviewed. This review also discussed various strategies that have been implemented to improve the properties of chitosan film, including using plasticizers and cross-linking agents, filling them with nanoparticles, fibers and whiskers and combining them with natural extracts and essential oils as well as with other natural and synthetic ingredients.

Keywords: chitosan, food preservation, edible film, essential oils, nanoparticle

1. INTRODUCTION

Packaging is very important in providing protection for products and ensuring food safety during distribution and during storage. Conventional food packaging in the form of plastic based on synthetic materials is the biggest source of environmental pollution because it cannot be degraded in nature. Therefore, bio-based and biodegradable materials have been widely studied to address this problem in recent years (Haghighi et al., 2020).

Along with the times, consumer demand for variety and quality of food products is increasing throughout the year. This fact has driven new developments in food packaging technology like never before to ensure the availability of safe and healthy food. The function of food packaging has shifted, where passive packaging is only limited to separating or blocking food

ingredients from the surrounding environment and minimizing or preventing exposure to spoilage-causing factors, including microorganisms, oxygen, temperature and humidity (Kumar et al., 2020). Although passive packaging can delay the detrimental effects of the environment on food products, it is not effective enough in maintaining the quality and safety of fresh, additive-free, nonprocessed or minimally processed foods during prolonged storage (Mexis and Kontominas, 2014).

One of the advanced technologies in food packaging is the application of active packaging. Based on European Regulation (EC) No. 450/2009, active packaging is defined as an interacting packaging system with food by deliberately inserting active components that can release or absorb substances into or from packaged food or the surrounding environment (European Commission, 2009). Active

packaging can work through different systems, including an active-releasing system (emitters) that adds compound to the headspace or to packaged food, and active-absorbing system (scavengers) work by removing unwanted compounds from food or its environment (Yildirim and R₂₄er, 2018).

Biodegradable polymers derived from renewable resources have been proven in many studies to be able to function as packaging materials for future generations, including chitosan. Chitosan is commercially produced from the deacetylation process of chitin (Verlee et al., 2017), which is the second most abundant polysaccharide in nature after cellulose (Salari et al., 2018) and is contained in crustaceans, insects, and fungi (Al Hoqani et al., 2020). The use of chitosan can solve the problem of plastic waste accumulation because it is biodegradable (Priyadarshi and Rhim, 2020), plus its antimicrobial activity which can fight bacteria and fungi that cause food spoilage (Duan et al., 2019), making it an attractive candidate for continuous development as an active food packaging material. However, chitosan also has several limitations. Like other natural polymers, chitosan has low mechanical and thermal stability. Chitosan also has high sensitivity to moisture that make it difficult to apply on an industrial scale (Elsabee and Abdou, 2013). One of the strategies that can be implemented to overcome these inherent drawbacks is to mix chitosan with other polymers to obtain their superior properties while minimizing their weaknesses (Haghighi et al., 2020). Chitosan can be blended with natural or synthetic polymers to enhance the mechanical and thermal properties of films.

This review article collects all the important articles related to the latest advances in chitosan as an active food packaging material and several strategies implemented to improve the quality of chitosan-based films.

2. POTENTIAL OF CHITOSAN

2.1 Source and Production

Chitin consists of three types of reactive functional groups, which are amino groups at C-2, and primary and secondary hydroxyl groups at the C-3 and C-6 positions, respectively (Kumar et al., 2020). Chitin is mainly present as the main constituent of the exoskeleton in marine invertebrates and insects, as well as a component of the cell wall in certain fungi (Al Hoqani et al., 2020).

The process of producing chitosan from animal wastes (skins and shells) generally carried out in two main steps, namely the extraction of chitin from the waste and followed by the conversion of chitin to chitosan (Priyadarshi and Rhim, 2020). Chitin extraction can be done in two ways, namely by using chemical method and biological method. Chemical method is widely used on a commercial scale because of its shorter processing time compared to biological method, although there are some disadvantages such

as unchemical and not environmentally friendly (Arbia et al., 2013).

Extraction of chitin from marine shell waste in the industrial level usually uses chemical methods. The most common industrial process applied for chitin extraction consists of three main steps: deproteinization of the raw material by addition of an alkaline solution, demineralization with the use of an acid solution, and finally discoloration of product by the addition of an alkaline solution (Muxica et al., 2017; Philibert et al., 2017). Biological method is safe and has become a very popular topic these days, but its use still limited to laboratory research (Kaur and Dh₁on, 2015).

Conversion of chitin to chitosan can be done through enzymatic or chemical processes. The enzymatic process employs chitin deacetylase enzyme which has complicated fermentation requirement in the preparation step (Priyadarshi and Rhim, 2020). The chemical conversion is preferred because of its lower cost and suitable for large quantity production (Younes and Rinaudo, 2015). The chemical deacetylation of chitin usually involves treatment using hydroxides at high temperatures. Under these conditions, the deacetylation occurs really fast (Muxica et al., 2017).

2.2 Deacetylation Degree and Antimicrobial Activity

The degree of deacetylation (removal of acetyl groups) (DD) is one of the most significant chemical characteristics of chitosan. The DD of chitosan is defined as the ratio of D-glucosamine units to the number of D-glucosamine and N-acetyl D-glucosamine units present in the chain (Kumar et al., 2020).

Chitosan can be claimed as the only natural polysaccharide that has antimicrobial activity against bacteria, fungi, and yeast. The nature of this antimicrobial activity depends on its cationic nature, deacetylation degree (DD), concentration, period of exposure, and the type of organism being tested (Priyadarshi and Rhim, 2020). In many studies, chitosan has been shown to have good antimicrobial property against various microorganisms such as Gram-positive and Gram-negative bacteria, filamentous fungi and yeast (Hosseinnejad and Jafari, 2016; Pan et al., 2015).

There are several proposed mechanisms for the antimicrobial activities of chitosan, but the exact mechanism is not yet clear (Kumar et al., 2020). The following are the mechanisms proposed by several researchers:

- (i) Interaction of negatively charged microbial cell membranes with positively charged amine groups in chitosan changes the barrier properties of the membrane, leading to leakage of intracellular contents, and ultimately to cell death (Hosseinnejad and Jafari, 2016).
- (ii) The chitosan layer on the food surface limits the gas exchange between the food and the outside environment. This causes a barrier to oxygen

transport, thus making the gas state confined to the aerobic microbes in the food, causing them to be eliminated (Dotto et al., 2015).

- (iii) Formation of a protective layer by chitosan on food surface, so that physically prevent it from attack by food spoilage microbes (Kumari et al., 2015)
- (iv) Chitosan forms an impermeable layer around bacterial cells and blocks the exchange of important solutes between the interior and the exterior resulting in failure of the metabolic system and ultimately cell death (Diez-Pascual and Diez-Vicente, 2015).

3. CHITOSAN FILMS

3.1 Chitosan Pure Films

Films derived from pure chitosan have been prepared and studied, without the use of other polymers. This chitosan-based film has also been applied to extend the shelf life of several food products such as vegetables, fruits, fish, and meat with different application methods such as spraying, immersing, coating, or wrapping (Suseno et al., 2014).

However, these films still need the addition of other materials to help film formation such as dilute acids, plasticizers, and emulsifiers (Priyadarshi dan Rhim, 2020). In the film fabrication, chitosan is usually dissolved in an acidic solutions, such as acetic acid or hydrochloric acid. Plasticizers such as glycerol are often used to increase the film flexibility and strength (Irawan et al., 2019), while emulsifiers have also been used for property enhancement such as Tween 20, Tween 80, Span 20, and Brij 56 (Rui et al., 2017; Zahid et al., 2012).

3.2 Chitosan and Its Blends Films with Natural and Synthetic Polymers

Chitosan has to be blended with other natural or synthetic polymers to improve the physical, thermal, mechanical, barrier, and optical features of films. Chitosan-based films were blended with biopolymers such as polysaccharides, proteins, lipids, and their derivatives to enhance its functionality as a packaging material for food. It has been found that chitosan can be blended with starch, cellulose, alginate, gelatin, protein, and some other biopolymers (Hasan et al., 2020; Deng et al., 2017; Arroyo et al., 2020; Hu et al., 2020; Samsalee and Sothornvit, 2011).

Chitosan has been blended with synthetic polymers such as polyvinyl alcohol, polyvinyl pyrrolidone, and polylactic acid to maintain the physical, mechanical, and biological properties of composite films (Yu et al., 2018; Lo'ay and Taher 2018; Fathima et al., 2018).

3.3 Chitosan Films with Plant Extracts and Natural Oils

Chitin, chitosan, and their derivatives have been reported to have natural antioxidant activity (Anraku

et al., 2018). Several studies have also resulted in increased antioxidant activity with the addition of active substances derived from plant extracts containing phenolic compounds (Kumar et al., 2020). Chitosan-based films which were impregnated with ginger essential oils showed a great potential use as active packaging for shelf life extension of food products (Irawan et al., 2019; Bonilla et al., 2018). An increase of film elasticity was also obtained after the incorporation of the oil (Bonilla et al., 2018).

Another study used tea extract containing polyphenols and showed more excellent antioxidant and antimicrobial activity compared to chitosan film alone (Zhang and Jiang, 2020). A study also reported the preparation of active film from chitosan and kombucha tea. It revealed that the addition of kombucha tea into chitosan films increase the antioxidant activity and water vapour permeability. Moreover, chitosan/kombucha tea film extended the shelf life of minced beef and retarded microbial growth significantly (Ashrafi et al., 2018).

Some plant extracts that have been used as additives in the manufacture of chitosan-based films include grapefruit seed extract (Wang et al., 2019), lemon essential oils (Jiang et al., 2020), cinnamon oil (Mohammadi et al., 2020), and turmeric essential oil (Li et al., 2019).

3.4 Chitosan Films with Nanoparticles

Metals and metal oxide nanoparticles have long been found to be applied as fillers in food packaging materials because of their extraordinary properties on antimicrobial and antioxidant activity which as a result can increase the shelf life of the product (Priyadarshi and Rhim, 2020). For those purposes, zinc oxide (ZnO), titanium dioxide (TiO₂), and silver (Ag) nanoparticles have been commercially used as antimicrobial agents in the preparation of chitosan-based active film (Amjadi et al., 2020; Wang et al., 2020; Cao et al., 2020; Qin et al., 2019; Lin et al., 2020; Kustiningsih et al., 2019).

In addition to nanoparticles in the form of metal and metal oxides, nanoclays or biopolymers in the form of nanoparticles can also be used such as nano-sized chitin, cellulose, and lignin (Priyadarshi dan Rhim, 2020).

4. CONCLUSION

Chitosan is a biopolymer whose availability is very abundant in nature and has enormous potential in the field of food packaging technology. Chitosan has superior properties, among others, it is easily degraded naturally and has excellent antimicrobial activity to fight bacterial and fungal proliferation which can cause food spoilage. To improve the properties of chitosan film as an active packaging for food products, it can be combined with other natural such as starch, cellulose, alginate, gelatin, and protein,

and/or synthetic polymers such as polyvinyl alcohol, polyvinyl pyrrolidone, and polylactic acid.

In order to improve antimicrobial and antioxidant activity, chitosan films can be enriched with plant extracts or essential oils. Nanomaterials like ZnO, TiO₂, and Ag are also frequently used to improve antimicrobial properties of packaging materials including chitosan film

5. ACKNOWLEDGMENTS

The authors acknowledge the Post-Graduate Programme of Chemical Engineering at University of Sultan Ageng Tirtayasa who provided financial support for the publication of this article.

6. REFERENCES

- Al Hoqani H.A.S., AL-Shaqsi N., Hossain M.A., Al Sibani M.A. 2020. Isolation and optimization of the method for industrial production of chitin and chitosan from Omani shrimp shell. *Carbohydrate Research*, Vol. 492, 108001.
- Amjadi S., Nazari M., Alizadeh S.A., Hamishehkar H. 2020. Multifunctional betanin nanoliposomes-incorporated gelatin/chitosan nanofiber/ZnO nanoparticles nanocomposite film for fresh beef preservation. *Meat Science*, Vol. 167, 108161.
- Anraku M., Gebicki J.M., Iohara D., Tomida H., Uekama K., Maruyama T., Hirayama F., Otagiri M. 2018. Antioxidant activities of chitosans and its derivatives in vitro and in vivo studies. *Carbohydrate Polymers*, Vol. 199, pp. 141-149.
- Arbia W., Arbia L., Adour L., Amrane A. 2013. Chitin extraction from crustacean shells using biological methods-A review. *Food Technology and Biotechnology*, Vol. 51 (1), 12.
- Arroyo B.J., Bezerra A.C., Oliveira L.L., Arroyo S.J., de Melo E.A., Santos A.M.P. 2020. Antimicrobial active edible coating of alginate and chitosan add ZnO nanoparticles applied in guavas (*Psidium guajava* L.). *Food Chemistry*, Vol. 309, 125566.
- Ashrafi A., Jokar M., Nafchi A.M. 2018. Preparation and characterization of biocomposite film based on chitosan and kombucha tea as active food packaging. *International Journal of Biological Macromolecules*, Vol. 108, pp. 444-454.
- Bonilla J., Poloni T., Lourenço R.V., Sobral P.J.A. 2018. Antioxidant potential of eugenol and ginger essential oils with gelatin/chitosan films. *Food Bioscience*, Vol. 23, pp. 107-114.
- Cao W., Yan J., Liu C., Zhang J., Wang H., Gao X., Yan H., Niu B., Li W. 2020. Preparation and characterization of catechol-grafted chitosan/gelatin/modified chitosan-AgNP blend films. *Carbohydrate Polymers*, Vol. 247, 116643.
- Deng Z., Jung J., Zhao Y., 2017. Development, characterization, and validation of chitosan adsorbed cellulose nanofiber (CNF) films as water resistant and antibacterial food contact packaging. *LWT - Food Science and Technology*, Vol. 83, pp. 132-140.
- Diez-Pascual A.M. and Diez-Vicente A.L. 2015. Antimicrobial and sustainable food packaging based on poly(butylene adipate-co-terephthalate) and electrospun chitosan nanofibers. *RSC Advances*, Vol. 5 (113), pp. 93095-93107
- Dotto G.L., Vieira M.L.G., Pinto L.A.A. 2015. Use of chitosan solutions for the microbiological shelf life extension of papaya fruits during storage at room temperature. *LWT-Food Science and Technology*, Vol. 64 (1), pp. 126-130.
- Duan C., Meng X., Meng J., Khan Md.I.H., Dai L., Khan A., An X., Zhang J., Huq T., Ni Y. 2019. Chitosan as A Preservative for Fruits and Vegetables: A Review on Chemistry and Antimicrobial Properties. *Journal of Bioresources and Bioproducts*, Vol. 4 (1), pp. 11-21.
- Elsabee M.Z. and Abdou E.S. 2013. Chitosan based edible films and coatings: A review. *Materials Science and Engineering C*, Vol. 33 (4), pp. 1819-1841
- European Commission. 2009. EU Guidance to the Commission Regulation (EC) No. 450/2009 of 29 May 2009 on Active and Intelligent Materials and Articles Intended to Come Into the Contact With Food (Text with EEA relevance), Official Journal of the European Commission, <https://eur-lex.europa.eu/LexUriServ/LexUriServ.do?uri=OJ:L:2009:135:0003:0011:EN:PDF>.
- Fathima P.E., Panda S.K., Ashraf P.M., Varghese T.O., Bindu J. 2018. Polylactic acid/chitosan films for packaging of Indian white prawn (*Fenneropenaeus indicus*). *International Journal of Biological Macromolecules*, Vol. 117, pp. 1002-1010.
- Haghighi H., Licciardello F., Fava P., Siesler H.W., Pulvirenti A. 2020. Recent advances on chitosan-based films for sustainable food packaging applications. *Food Packaging and Shelf Life*, Vol. 26, 100551.
- Hasan M., Rusman R., Khaldun I., Ardana L., Mudatsir M., Fansuri H. 2020. Active edible sugar palm starch-chitosan films carrying extra virgin olive oil: Barrier, thermo-mechanical, antioxidant, and antimicrobial properties. *International Journal of Biological Macromolecules*, Vol. 163, pp. 766-775.
- Hosseinnejad M. and Jafari S.M. 2016. Evaluation of different factors affecting antimicrobial properties of chitosan. *International Journal of Biological Macromolecules*, Vol. 85, pp. 467-475.
- Hu H., Yao X., Qin Y., Yong H., Liu J. 2020. Development of multifunctional food packaging by incorporating betalains from vegetable amaranth (*Amaranthus tricolor* L.) into quaternary ammonium chitosan/fish gelatin blend films. *International Journal of Biological Macromolecules*, Vol. 159, pp. 675-684.
- Irawan A., Barleany D.R., Jayanudin, Yulvianti M., Maulana R.C., Yulian L. 2019. Chitosan active films containing red ginger extract for shelf-life extension and quality retention of milkfish (*Chanos chanos*). *AIP Conference Proceeding*, 2085, 020032.
- Jiang Y., Lan W., Sameen D.E., Ahmed S., Qin W., Zhang Q., Chen H., Dai J., He L., Liu Y. 2020. Preparation and characterization of grass carp collagen-chitosan-lemon essential oil composite films for application as food packaging. *International Journal of Biological Macromolecules*, Vol. 160, pp. 340-351.
- Kaur S. and Dhillon G.S. 2015. Recent trends in biological extraction of chitin from marine shell wastes: a review. *Critical Reviews in Biotechnology*, Vol. 35 (1), pp. 44-61.
- Kumar S., Mukherjee A., Dutta J. 2020. Chitosan based nanocomposite films and coatings: Emerging antimicrobial food packaging alternatives. *Trends in Food Science & Technology*, Vol. 97, pp. 196-209.
- Kumari P., Barman K., Patel V.B., Siddiqui M.W., and Kole B. 2015. Reducing postharvest pericarp browning and preserving health promoting compounds of litchi fruit by combination treatment of salicylic acid and chitosan. *Scientia Horticulturae*, Vol. 197, pp. 555-563.
- Kustiningsih I., Ridwan A., Abriyani D., Syairazy M., Kurniawan T., Barleany D. R. 2019. Development of Chitosan-TiO₂ Nanocomposite for Packaging Film and its Ability to Inactivate *Staphylococcus aureus*. *Oriental Journal of Chemistry*, Vol. 35 (3), pp. 1132-1137.
- Li Z., Lin S., An S., Liu L., Hu Y., Wan L. 2019. Preparation, characterization and anti-aflatoxigenic activity of chitosan packaging films incorporated with turmeric essential oil. *International Journal of Biological Macromolecules*, Vol. 131, pp. 420-434
- Lin D., Yang Y., Wang J., Yan W., Wu Z., Chen H., Zhang Q., Wu D., Qin W., Tu Z. 2020. Preparation and characterization of TiO₂-Ag loaded fish gelatin-chitosan antibacterial composite film for food packaging. *International Journal of Biological Macromolecules*, Vol. 154, pp. 123-133
- Lo'ay A.A. and Taher M.A. 2018. Effectiveness salicylic acid blending in chitosan/PVP biopolymer coating on antioxidant enzyme activities under low storage temperature stress of 'Banat' guava fruit. *Scientia Horticulturae*, Vol. 238, pp. 343-349.
- Mexis S.F. and Kontominas M.G. 2014. Packaging: Active Food Packaging. Reference Module in Food Science Encyclopedia of Food Microbiology (Second Edition), Elsevier Ltd, Amsterdam, Netherlands.
- Mohammadi M., Mirabzadeh S., Shahvalizadeh R., Hameshehkar H. 2020. Development of novel active packaging films based on whey protein isolate incorporated with chitosan nanofiber and nano-formulated cinnamon oil. *International Journal of Biological Macromolecules*, Vol. 149, pp. 11-20.

- Muxica A., Etxabide A., Uranga J., Guerrero P., de la caba K. 2017. Chitosan as a bioactive polymer: Processing, properties and applications: Review. *International Journal of Biological Macromolecules*, Vol. 105, pp. 1358-1368.
- Pan Y., Huang X., Shi X., Zhan Y., Fan G., Pan S. 2015. Antimicrobial application of nanofibrous mats self-assembled with quaternized chitosan and soy protein isolate. *Carbohydrate Polymers*, Vol. 133, pp. 229-235.
- Philibert T., Lee B.H., Fabien N. 2017. Current status and new perspectives on chitin and chitosan as functional biopolymers. *Appl. Biochem. Biotechnol.*, Vol. 181, pp. 1314-1337.
- Priyadarshi R. and Rhim J-W. 2020. Chitosan-based biodegradable functional films for food packaging applications. *Innovative Food Science and Emerging Technologies*, Vol. 62, 102346.
- Qin Y., Liu Y., Yuan L., Yong H., Liu J. 2019. Preparation and characterization of antioxidant, antimicrobial and pH-sensitive films based on chitosan, silver nanoparticles and purple corn extract. *Food Hydrocolloids*, Vol. 96, pp. 102-111.
- Rui L., Xie M., Hu B., Zhou L., Yin D., Zeng X. 2017. A comparative study on chitosan/gelatin composite films with conjugated or incorporated gallic acid. *Carbohydrate Polymers*, Vol. 173, pp. 473-481.
- Salari M., Khiabani M.S., Mokarram R.R., Ghanbarzadeh B., Kafil H.S. 2018. Development and evaluation of chitosan based active nanocomposite films containing bacterial cellulose nanocrystals and silver nanoparticles. *Food Hydrocolloids*, Vol. 84, pp. 414-423.
- Samsalee N. and Sothornvit R. 2019. Development and characterization of porcine plasma protein-chitosan blended films. *Food Packaging and Shelf Life*, Vol. 22, 100406.
- Suseno N., Savitri E., Sapei L., Padmawijaya K.S., 2014. Improving Shelf-life of Cavendish Banana Using Chitosan Edible Coating. *Procedia Chemistry*, Vol. 9, pp. 113-120.
- Verlee A., Mincke S., Stevens C.V., 2017. Recent developments in antibacterial and antifungal chitosan and its derivatives. *Carbohydrate Polymers*, Vol. 164, pp. 268-283.
- Wang C., Chang T., Dong S., Zhang D., Ma C., Chen S., Li H. 2020. Biopolymer films based on chitosan/potato protein/linseed oil/ZnO NPs to maintain the storage quality of raw meat. *Food Chemistry*, Vol. 332, 127375.
- Wang K., Lim P.N., Tong S.Y, Thian E.S. 2019. Development of grapefruit seed extract-loaded poly(ϵ -caprolactone)/chitosan films for antimicrobial food packaging. *Food Packaging and Shelf Life*, Vol. 22, 100396.
- Yildirim S. and Röcker B. 2018. *Active Packaging. Nanomaterials for Food Packaging Materials, Processing Technologies, and Safety Issues*, Micro and Nano Technologies, Elsevier Ltd, Amsterdam, Netherlands.
- Younes I. and Rinaudo M. 2015. Chitin and chitosan preparation from marine sources: Structure, properties and applications. *Mar. Drugs*, Vol. 13, pp. 1133-1174.
- Yu Z., Li B., Chu J., Zhang P. 2018. Silica in situ enhanced PVA/chitosan biodegradable films for food packages. *Carbohydrate Polymers*, Vol. 184, pp. 214-220.
- Zahid N., Ali A., Manickam S., Siddiqui Y., Maqbool M. 2012. Potential of chitosan-loaded nanoemulsions to control different *Colletotrichum* spp. and maintain quality of tropical fruits during cold storage. *Journal of Applied Microbiology*, Vol. 113 (4), pp. 925-939.
- Zhang W. and Jiang W. 2020. Antioxidant and antibacterial chitosan film with tea polyphenols-mediated green synthesis silver nanoparticle via a novel one-pot method. *International Journal of Biological Macromolecules*, Vol. 155, pp. 1252-12

Emerging Trends in the Development of Chitosan Films for Active Food Packaging

ORIGINALITY REPORT

21 %
SIMILARITY INDEX

15 %
INTERNET SOURCES

15 %
PUBLICATIONS

7 %
STUDENT PAPERS

PRIMARY SOURCES

1 dalspace.library.dal.ca 1 %
Internet Source

2 Submitted to Universidad de Cartagena 1 %
Student Paper

3 scindeks-clanci.ceon.rs 1 %
Internet Source

4 João Pires, Camila Damásio de Paula, Victor Gomes Lauriano Souza, Ana Luísa Fernando, Isabel Coelho. "Understanding the Barrier and Mechanical Behavior of Different Nanofillers in Chitosan Films for Food Packaging", Polymers, 2021 1 %
Publication

5 rucore.libraries.rutgers.edu 1 %
Internet Source

6 repository.lppm.unila.ac.id 1 %
Internet Source

7 eprints.iums.ac.ir 1 %
Internet Source

8	sidimas.mercubuana.ac.id Internet Source	1 %
9	"Sustainable Polymer Composites and Nanocomposites", Springer Nature, 2019 Publication	1 %
10	Nasreddine Benbettaïeb, Frédéric Debeaufort, Thomas Karbowiak. "Bioactive edible films for food applications: mechanisms of antimicrobial and antioxidant activity", Critical Reviews in Food Science and Nutrition, 2018 Publication	1 %
11	Submitted to Sri Lanka Institute of Information Technology Student Paper	1 %
12	ir.jkuat.ac.ke Internet Source	1 %
13	journals.lww.com Internet Source	1 %
14	nofima.brage.unit.no Internet Source	1 %
15	"Chitin and Chitosan", Wiley, 2019 Publication	1 %
16	Submitted to Durban University of Technology Student Paper	1 %

Submitted to Unizin, LLC

17

Student Paper

1 %

18

Asgar Ali, Nurasyikin Mohd Noh, Maysoun A. Mustafa. "Antimicrobial activity of chitosan enriched with lemongrass oil against anthracnose of bell pepper", Food Packaging and Shelf Life, 2015

Publication

<1 %

19

elib.sfu-kras.ru

Internet Source

<1 %

20

mural.maynoothuniversity.ie

Internet Source

<1 %

21

www.scirp.org

Internet Source

<1 %

22

Fatih Ozogul, Martina Cagalj, Vida Šimat, Yesim Ozogul et al. "Recent developments in valorisation of bioactive ingredients in discard/seafood processing by-products", Trends in Food Science & Technology, 2021

Publication

<1 %

23

Katarzyna Samborska, Sareh Boostani, Mansoureh Geranpour, Hamed Hosseini et al. "Green biopolymers from by-products as wall materials for spray drying microencapsulation of phytochemicals", Trends in Food Science & Technology, 2021

Publication

<1 %

24 Micaela Degli Esposti, Davide Morselli, Fabio Fava, Lorenzo Bertin, Fabrizio Cavani, Davide Viaggi, Paola Fabbri. "The role of biotechnology in the transition from plastics to bioplastics: an opportunity to reconnect global growth with sustainability", FEBS Open Bio, 2021
Publication

25 Suyeon Jeong, Hyun-Gyu Lee, Chi Heung Cho, SeungRan Yoo. "Characterization of multi-functional, biodegradable sodium metabisulfite-incorporated films based on polycarprolactone for active food packaging applications", Food Packaging and Shelf Life, 2020
Publication

26 ebin.pub
Internet Source

27 ir.library.oregonstate.edu
Internet Source

28 link.springer.com
Internet Source

29 tudr.thapar.edu:8080
Internet Source

30 Ashish A. Kadam, Suman Singh, Kirtiraj K. Gaikwad. "Chitosan based antioxidant films incorporated with pine needles (Cedrus

deodara) extract for active food packaging applications", Food Control, 2021

Publication

31

DG Braga, PGF Bezerra, ABFD Lima, HA Pinheiro, LG Gomes, AS Fonseca, L Bufalino. "Chitosan-based films reinforced with cellulose nanofibrils isolated from MART ", Polymers from Renewable Resources, 2021

Publication

<1 %

32

Pablo R. Salgado, Luciana Di Giorgio, Yanina S. Musso, Adriana N. Mauri. "Recent Developments in Smart Food Packaging Focused on Biobased and Biodegradable Polymers", Frontiers in Sustainable Food Systems, 2021

Publication

<1 %

33

Surinder Kaur, Gurpreet Singh Dhillon. "Recent trends in biological extraction of chitin from marine shell wastes: a review", Critical Reviews in Biotechnology, 2013

Publication

<1 %

34

aip.scitation.org

Internet Source

<1 %

35

journals.pan.pl

Internet Source

<1 %

36

repo.ur.krakow.pl

Internet Source

<1 %

37	www.ecorfan.org Internet Source	<1 %
38	www.frontiersin.org Internet Source	<1 %
39	www.mdpi.com Internet Source	<1 %
40	www.scielo.br Internet Source	<1 %
41	N Vishnu Priya, U G Vinitha, Muthuraman Meenakshi Sundaram. "Preparation of chitosan-based antimicrobial active food packaging film incorporated with <i>Plectranthus amboinicus</i> essential oil", <i>Biocatalysis and Agricultural Biotechnology</i> , 2021 Publication	<1 %
42	Shuva Bhowmik, Dominic Agyei, Azam Ali. "Bioactive chitosan and essential oils in sustainable active food packaging: Recent trends, mechanisms, and applications", <i>Food Packaging and Shelf Life</i> , 2022 Publication	<1 %
43	www.e-fas.org Internet Source	<1 %

Exclude quotes On

Exclude matches Off

Exclude bibliography On